

Product Description**ITEM CODE****BML_F010**

Grade

HDPE Polyethylene

Application

Extursion Process

Color

Natural

Typical Data

TEST ITEM	UNIT	METHOD	VALUE
MFI (190°C-5 kg)	gr/10min	ISO 1133	1.2±0.01
Density	gr/cm ³	ISO 1183	0.950±0.005
Impact strength (23°C)	Mj/mm ²	ISO 179/1eA	9_11

Remarks

Package: Plastic bages 25±0.1kg

Storage: In manner to prevent of direct exposure of sun light or heat the storage area should be dry and preferably don't exceed 50°C. We do not give warranty to bad storage conditions leads to quality deterioration and inadequate product performace.