

**Product Description****ITEM CODE****FSH-T014**

Grade

LLDPE Polyethylene

Application

Blown Film

Color

Natural

**Typical Data**

TEST ITEM	UNIT	METHOD	VALUE
MFI (190°C-2.16 kg)	gr/10min	ISO 1133	0.7±0.01
Density	gr/cm <sup>3</sup>	ISO 1183	0.920±0.005
Elongation	%	ISO 527	500/900
Tensile Stress at Yield	MPA	ISO 527	11±2
Vicat Softening Point	°C	ASTM D-1525	93

**Remarks**

Package: Plastic bages 25±0.1kg

Storage: In manner to prevent of direct exposure of sun light or heat the storage area should be dry and preferably don't exceed 50°C. We do not give warranty to bad storage conditions leads to quality deterioration and inadequate product performace.