

Product Description**ITEM CODE****FST-T013**

Grade

LLDPE Polyethylene

Application

Blown Film

Color

Natural

Typical Data

TEST ITEM	UNIT	METHOD	VALUE
MFI (190°C-2.16 kg)	gr/10min	ISO 1133	1±0.05
Density	gr/cm ³	ISO 1183	0.920±0.002
Elongation	%	ISO 527	600/900
Tensile Stress at Yield	MPA	ISO 527	11±2
Elmendorf Tear	gr	ASTM D-1922	145/370

Remarks

Package: Plastic bages 25±0.1kg

Storage: In manner to prevent of direct exposure of sun light or heat the storage area should be dry and preferably don't exceed 50°C. We do not give warranty to bad storage conditions leads to quality deterioration and inadequate product performace.