

Product Description**ITEM CODE****RMD_3840_M014**

Grade

MD/HDPE POLYETHYLENE

Application

rotation Molding

Color

Blue

Typical Data

TEST ITEM	UNIT	METHOD	VALUE
MFI (190°C-2.16 kg)	gr/10min	ISO 1133	3±0.2
Density	gr/cm ³	ISO 1183	0.938±0.002
Elongation	%	ASTM D-638	900
Tensile Stress at Yield	MPA	ASTM D-638	15±2
Vicat Softening Point	°c	ASTM D-1525	115

Remarks

Package: Plastic bages 25±0.1kg

Storage: In manner to prevent of direct exposure of sun light or heat the storage area should be dry and preferably don't exceed 50°C. We do not give warranty to bad storage conditions leads to quality deterioration and inadequate product performace.